

ISO 9001:2000, ISO 14001:2004 AND OHSAS 18001:2007 REGISTERED

SIVACO Ontario

a Division of SIVACO Wire Group L.P.

330 Thomas Street PO Box 220 Ingersoll, Ontario CANADA N5C 3K5

(519) 485-4150 Fax (519) 485-3039

Physical Test Report

WORK ORDER **047693**

LOT NUMBER W16552

SALES ORDER / RLS 028190 / 1 CERT ID / REV 00009612 / 01

SOLD TO

Windsor Machine & Stamping (US) Ltd 26655 NorthLine Road Taylor, MI 48180 United States Attn: Quality Assurance

CUSTOMER P.C	R P.O. CUSTOMER PART 12.00-1018 IQ			QUANT 8,030 I					-		
SPECIFICATION 12.00mm (0.4)18120-01 8 IQ, Clear	n/Coat, Clea	an/Lime, W	indsor M	achine	& Star	nping L	td, 7213.91	.6000	
CUSTOMER RE	QUIREMENT	-S									
			(Chemical (value of 9) = n/a)					
C .17	Mn .69	P .014	s .011	si .19	Cu .03	N .0		Cr .060	Mo .007	sn .004	A1 .002
В .0001	v .005	N .0028									
				Dim	ensional						
TEST Diameter (inch)		<u>L</u> iı	<u>INITS</u> n				<u>нідн</u> .473		<u>LOW</u> .470	<u>AVERAGE</u> 0.471	
				End of 0	Certification						

I attest that the results are a true and correct copy of the records prepared and maintained by SIVACO Ontario in compliance with the requirements of the cited specification. Chemistry is as reported by the rod / bar supplier. This test report cannot be reproduced or distributed, except in full, without the written permission of SIVACO Ontario.

Authorized by: Graham Benoit, QA Manager