

ISO 9001:2008, ISO 14001:2004 AND OHSAS 18001:2007 REGISTERED

SIVACO Ontario

a Division of SIVACO Wire Group L.P.

330 Thomas Street PO Box 220 Ingersoll, Ontario CANADA N5C 3K5

(519) 485-4150 Fax (519) 485-3039

Physical Test Report

WORK ORDER **057893**

HEAT NUMBER **A02618**

SALES ORDER / RLS 035071 / 8 CERT ID / REV 00018648 / 01

SOLD TO

Windsor Machine & Stamping (US) Ltd 26655 NorthLine Road Taylor, MI 48180 United States

Attn: Quality Assurance

JSTOMER P.	0. (CUSTOMER F	PART	QUANTITY 6,602 lbs				00044	_	_	SHIPMENT DATE 11/01/2010	
•		•		lean/Lime	(MOD), W	indsor M	achin	e & Sta	amping (U	S, 7213.91	.6000	
OTOWIER RE	LQUINLIVI			Chemical	(value of 9	9 = n/a)						
C .0900	Mn .5000	P .0140	s .0130	si .1700	Cu .2300	Ni .0900	.1	Cr .300	Mo .0210	Sn .0120	A1 .0030	
B .0000	v .0010	N .0080										
.0000	.0010	.0000										

I attest that the results are a true and correct copy of the records prepared and maintained by SIVACO Ontario in compliance with the requirements of the cited specification. Chemistry is as reported by the rod / bar supplier. This test report cannot be reproduced or distributed, except in full, without the written permission of SIVACO Ontario.

Authorized by: Graham Benoit, QA Manager