

ISO 9001:2008, ISO 14001:2004 AND OHSAS 18001:2007 REGISTERED

SIVACO Ontario a Division of SIVACO Wire Group L.P.

330 Thomas Street PO Box 220 Ingersoll, Ontario CANADA N5C 3K5

(519) 485-4150 Fax (519) 485-3039

Physical Test Report

WORK ORDER 073425

HEAT NUMBER A08676 SALES ORDER / RLS 045954 / 3 CERT ID / REV 00034618 / 01

SOLD TO

Windsor Machine & Stamping (US) Ltd 26655 NorthLine Road Taylor, MI 48180 United States Attn: Quality Assurance

CUSTOMER P.O. CUSTOMER PART Polymer				QUAN 3,950			ADING NO 00052323		IPMENT DAT /03/2012		
SPECIFICATIO 0.5650" (14. Non-Alloy V C=>0.25% a	.351mm) 15 Vire, Heat 1	reated		n/Phos/Po	lymer, Win	dsor Mac	thine 8	& Stamping Lto	d, 7217.10.	8010	
CUSTOMER R	EQUIREMENT	rs									
				Chemical	(value of 9) = n/a)					
C .3700	Mn 1.3800	P .0090	s .0120	si .2300	Cu .1600	Ni .0600	.10	Cr Mo 00 .0180	Sn .0090	Al .0040	
B .0001	v .0040	N .0086									
				Mechan	ical - Sum	mary					
<u>TEST</u> Diameter (inch)		<u>UNITS</u> in				<u>HIGH</u> .564		<u>LOW</u> .564		<u>AVERAGE</u> 0.564	
Tensile (psi	i)	psi			???????????????????????????????????????		?? 7	???????????????????????????????????????	? ??????	???????????????????????????????????????	
				End of	f Certification						

I attest that the results are a true and correct copy of the records prepared and maintained by SIVACO Ontario in compliance with the requirements of the cited specification. Chemistry is as reported by the rod / bar supplier. This test report cannot be reproduced or distributed, except in full, without the written permission of SIVACO Ontario.

Authorized by: Gary Allard, QA Manager