

ISO 9001:2008, ISO 14001:2004 AND OHSAS 18001:2007 REGISTERED

SIVACO Ontario

a Division of SIVACO Wire Group L.P.

330 Thomas Street PO Box 220 Ingersoll, Ontario CANADA N5C 3K5

(519) 485-4150 Fax (519) 485-3039

Physical Test Report

WORK ORDER **079940**

HEAT NUMBER W31819

SALES ORDER / RLS 050406 / 7 CERT ID / REV 00041057 / 01

SOLD TO

Windsor Machine & Stamping (US) Ltd 26655 NorthLine Road Taylor, MI 48180 United States

Attn: Quality Assurance

		IROQUIOS			8,056 lbs 4 0005515			010/	7 01/03/2013		
SPECIFICATION 3.00mm (0.1) Hot Rolled F	5118") 101							tamping Lt	d, 7213.9 [.]	1.6000	
USTOMER RE	EQUIREMENT	TS									
				Chemical	(value of 9) = n/a)					
C .1600	Mn .7400	P .0050	s .0100	si .1700	Cu .0400	Ni .0500	Cr .0400	Mo .0070	Sn .0030	Al .0010	
B .0002	V .0020	N .0043									
				Mechan	ical - Sum	mary					
TEST Diameter (inch)		<u>UNITS</u> in				<u>нідн</u> . 511		<u>LOW</u> .510		AVERAGE 0.511	
Tensile (psi)		psi				68527		68259		68393	
				End of	Certification						

I attest that the results are a true and correct copy of the records prepared and maintained by SIVACO Ontario in compliance with the requirements of the cited specification. Chemistry is as reported by the rod / bar supplier. This test report cannot be reproduced or distributed, except in full, without the written permission of SIVACO Ontario.

Authorized by: Gary Allard, QA Manager